

Copy of Letter from CMP Chugoku

CMP CHUGOKU

CHUGOKU PAINTS B.V.
Sluisweg 12, 4794 SW Heijningen, The Netherlands
Telephone: +31167526100

No. JM-202311-01
17th Nov, 2023

Messrs. Clean for Cargo

Resistance of Masava Tank Cleaner Solid

The attached test report from BSO Svendborg d.d. November 10, 2023 is accepted. The product Masava Tank Cleaner Solid of company Clean for Cargo can be used in tanks coated with EPICON T-800, provided that the use of the cleaner is in accordance with the maximum range for mixing percent, temperatures and time stated in the test.

Sincerely yours,
CHUGOKU PAINTS B. V.



Junichiro Murakami
Manager Technical

MASAVA TANK CLEANER SOLID TEST

To Whom it may concern

Svendborg 10/11/2023

On behalf of MASAVA KEMI


BSO Svendborg has tested MASAVA TANK CLEANER SOLID with CMP EPICON T-800

Test result:

Product tested	MASAVA TANK CLEANER SOLID	HS Code: 34029090000
Coating tested	CMP EPICON T-800 RED BROWN	Batch: C4309021
	CMP EPICON HARDENER	Batch: C4309020
	Panel applied 320 μ DFT by brush. Heat cured for 6 hours at 80°C	

Test method	The test panels were partially submerged into a solution of Tank Cleaner Solid then heated to 75°C for at minimum of 30 minutes. The panels were then rinsed with fresh water and visually examined for discolouring and coating degradation.
--------------------	--

Panel	Concentration	Temp.	Duration	Discolouring	Coating degradation
1	0,50% TCS mixed with Fresh water	75°C	36 minutes	None observed	None observed
2	0,25% TCS mixed with Fresh water	75°C	31 minutes	None observed	None observed



Bo Sørensen
Coating Advisor
BSO Svendborg
Østre Havnevej 2,3rd floor
DK -5700 Svendborg



*Enjoy the view of
a beautiful ship*